AMENDMENTS TO THE CLAIMS

This listing of claims will replace all prior versions and listings of claims in the application:

LISTING OF CLAIMS:

1. (currently amended): Method for producing ~~a workpiece or~~ a plate of steel which is resistant to abrasion and whose chemical composition comprises, by weight:

$$0.24\% \leq C < 0.35\%$$

$$0\% \leq Si \leq 2\%$$

$$0\% \leq Al \leq 2\%$$

$$0.5\% \leq Si + Al \leq 2\%$$

$$0\% \leq Mn \leq 2.5\%$$

$$0\% \leq Ni \leq 5\%$$

$$0\% \leq Cr \leq 5\%$$

$$0\% \leq Mo \leq 1\%$$

$$0\% \leq W \leq 2\%$$

$$0.1\% \leq Mo + W/2 \leq 1\%$$

$$0\% \leq B \leq 0.02\%$$

$$0\% \leq Ti \leq 1.1\%$$

$$0\% \leq Zr \leq 2.2\%$$

$$\text{~~0.35\%~~}\underline{0.5\%} < Ti + Zr/2 \leq 1.1\%$$

$$0\% \leq S \leq 0.15\%$$

$$N < 0.03\%$$

- optionally ~~from 0%~~<u>up</u> to 1.5% of copper,

- optionally at least one element selected from Nb, Ta and V at contents such that Nb/2 + Ta/4 + V $\leq$ 0.5%,

- optionally at least one element selected from Se, Te, Ca, Bi, Pb at contents which are less than or equal to 0.1%,

the balance being iron and impurities resulting from the production operation, the chemical composition further complying with the following relationships:

$$C^* = C - Ti/4 - Zr/8 + 7xN/8 \geq 0.095\%$$

and:

$$1.05xMn + 0.54xNi + 0.50xCr + 0.3x(Mo + W/2)^{1/2} + K > 1.8$$

with: K = 0.5 if B $\geq$ 0.0005% and K = 0 if B < 0.0005%.

according to which the plate is subjected to a thermal quenching processing operation which is carried out in the heat for ~~forming~~ rolling in the hot state ~~and, for example, rolling heat,~~ or after austenitization by reheating in a furnace, in order to carry out the quenching:

- ~~the workpiece or~~ the plate is cooled at a mean cooling rate greater than 0.5°C/s between a temperature greater than AC₃ and a temperature of from approximately T = 800 − 270xC* - 90xMn − 37xNi − ~~70XCr~~ 70xCr − 83x(Mo + W/2), to T-50°C,

- ~~the workpiece or~~ the plate is then cooled at a mean core cooling rate Vr < 1150xep^{-1.7} and greater than 0.1°C/s between the temperature T and 100°C, ep being the thickness of the plate expressed in mm,

- ~~the workpiece or~~ the plate is cooled as far as ambient temperature and optionally planishing is carried out.

2. (currently amended): Method according to claim 1, ~~characterized in that~~ wherein:

$$1.05xMn + 0.54xNi + 0.50xCr + 0.3x(Mo + W/2)^{1/2} + K > 2.$$

3. (canceled).

4. (currently amended): Method according to ~~any one of claims 1 to 3~~claim 1, ~~characterized in that~~wherein:

$$C^* \geq 0.12\%.$$

5. (currently amended): Method according to ~~any one of claims 1 to 4~~claim 1, ~~characterized in that~~wherein:

$$Si + Al \geq 0.7\%.$$

6. (currently amended): Method according to ~~any one of claims 1 to 5~~claim 1, ~~characterized in that~~wherein tempering is further carried out at a temperature which is less than or equal to 350°C.

7. (currently amended): Method according to ~~any one of claims 1 to 6~~claim 1, ~~characterized in that~~wherein, the chemical composition of the steel is obtained by a melting process during which or after ~~in order to add titanium to the steel, the liquid~~the steel is placed in contact with a slag containing titanium and the titanium of the slag is caused to diffuse ~~slowly~~ in the ~~liquid~~ steel which is in a liquid state.

8. (withdrawn): Workpiece, and in particular a plate, of steel which is resistant to abrasion and whose chemical composition comprises, by weight:

$$0.24\% \leq C < 0.35\%$$

$$0\% \leq Si \leq 2\%$$

$$0\% \leq Al \leq 2\%$$

$$0.5\% \leq Si + Al \leq 2\%$$

$$0\% \leq Mn \leq 2.5\%$$

$$0\% \leq Ni \leq 5\%$$

$$0\% \leq Cr \leq 5\%$$

$$0\% \leq Mo \leq 1\%$$

$$0\% \leq W \leq 2\%$$

$$0.1\% \leq Mo + W/2 \leq 1\%$$

$$0\% \leq B \leq 0.02\%$$

$$0\% \leq Ti \leq 1.1\%$$

$$0\% \leq Zr \leq 2.2\%$$

$$0.35\% < Ti + Zr/2 \leq 1.1\%$$

$$0\% \leq S \leq 0.15\%$$

$$N < 0.03\%$$

- optionally from 0% to 1.5% of copper,

- optionally at least one element selected from Nb, Ta and V at contents such that $Nb/2 + Ta/4 + V \leq 0.5\%$,

- optionally at least one element selected from Se, Te, Ca, Bi, Pb at contents which are less than or equal to 0.1%,

the balance being iron and impurities resulting from the production operation, the chemical composition further complying with the following relationships:

$$C - Ti/4 - Zr/8 + 7xN/8 \geq 0.095\%$$

and:

6

$$1.05xMn + 0.54xNi + 0.50xCr + 0.3x(Mo + W/2)^{1/2} + K > 1.8$$

with: $K = 0.5$ if $B \geq 0.0005\%$ and $K = 0$ if $B < 0.0005\%$,

the steel having a martensitic or martensitic/bainitic structure, the structure containing from 5% to 20% of retained austenite and carbides.

9. (withdrawn): Workpiece according to claim 8, characterized in that:

$$1.05xMn + 0.54xNi + 0.50xCr + 0.3x(Mo + W/2)^{1/2} + K > 2.$$

10. (withdrawn): Workpiece according to claim 8 or claim 9, characterized in that:

$$Ti + Zr/2 \geq 0.4\%.$$

11. (withdrawn): Workpiece according to any one of claims 8 to 10, characterized in that:

$$C^* \geq 0.12\%.$$

12. (withdrawn): Workpiece according to any one of claims 8 to 11, characterized in that:

$$Si + Al \geq 0.7\%$$

13. (withdrawn): Workpiece according to any one of claims 8 to 12, characterized in that it is a plate having a thickness of from 2 mm to 150 mm.